

## 23330 Yellow, greenish

Chemical group: Azomethine Cu complex  
C.I. Number: Pigment Yellow 129, 48042  
Physical form: powder

Azomethine Cu complex with improved gloss, especially suited for metallic automotive finishes.

### Physical Data:

Density: 1.66 g/cm<sup>3</sup>  
Bulk volume: 5.0 l/kg  
Specific surface: 91 m<sup>2</sup>/g  
Oil absorption: 51 g / 100 g

Thermal resistance: 150°C (302°F) / 30 min: 5  
200°C (392°F) / 10 min: 5

Fastness to overcoating:  
- Cellulose nitrate paint: baking finish, 130°C (266°F) / 30 min: 5

Resistance to solvents:  
- Butyl acetate: 3 – 4  
- Ethanol: 4  
- Methylene ketone: 3 – 4  
- Water: 5  
- Xylene: 4  
- White spirit: 5

Resistance to chemicals:  
- Acid: 4 – 5  
- Alkali: 5

Suitability for industries:  
- Automotive  
- General industrial

Suitability for applications:  
- Baking finishes  
- Air-drying

Potentially suitable for applications:  
- Acrylic / isocyanate  
- Acid-curable