

60480 Shellac Ruby, ruby colored, light, wax-free

SPECIFICATION

<i>Data</i>	<i>Method of Analysis</i>	<i>Specification</i>	<i>Unit</i>	<i>Results</i>
Acid value	DIN 53402	60 - 75	[mg KOH/g]	68
Saponification value	DIN 53401	175 - 240	[mg KOH/g]	188
Loss on drying	ISO 56/II - 1979	≤ 2	[%]	1.2
Color index	Lovibond PRS-Scale 20% in Ethanol	≥ 9		9
Wax *	USP	≤ 0,2	[%]	< 0.2
Lead *	USP	≤ 2	[ppm]	< 2
Colophony	USP	conforms		conforms
Melting temperature	ANSI/ASTM D 3451-76 (Kofler-Heizbank)	65 - 77	[°C]	conforms

Comment:

The above information is derived from our quality control. It does not relieve the purchaser from examining the product upon delivery and gives no assurance of stability of the product for any particular purpose.