

73900 Tung Oil

Tung oil is made from the pressed seed from the nut of the tung tree.

Technical Information

Relative density (20°C)	0.930 – 0.939
Refractive index (20°C)	1.513 – 1.522
Acid value	approx. 5
Iodine value	205 - 215
Saponification value	189 - 198
Gel test	15 – 22 min.