

50800 Gold Glitter

Material:	Aluminium foil
Al %:	> 90 %
Particle size:	100 x 100 micron
Color:	gold
Thickness:	19 (+/- 10%) micron
Cut:	square
Solvent resistance:	yes (5 minutes in MEK)
Heat stability:	220°C

Stability

Medium	Condition	Result
Temperature	up to 220°C	stable
MEK (Methylethyl ketone, 99 %)	15 min.	stable
Isopropanol (25 %)	15 min.	stable
Isopropanol (70 %)	15 min.	stable
Demineralized H ₂ O	3 months	stable

Storage Condition

Store product dry and at room temperature in a closed (original) container.

Recommended storage time: max. 2 years

We definitely recommend tests prior to the final application.