


23493 Gubbio Red

The lightfastnesses (scale 1-8) of Gubbio Red are very good, with values of 8 in the solid and 7-8 in the mixtures. The weather resistance of the mixtures (scale 1-5) is 3-4 and is therefore not maximum. At higher humidity, lightening (due to interaction with titanium dioxide) may occur. For this reason, Gubbio Red is not recommended for outdoor use, for example in Australia.

Raman spectrum of 23493:

(Bron: MR PHSG, 2017)



— Sample Spectrum