

23730 Quindo Violet light, PV 55

An intense red shade violet quinacridone pigment with unique color space, high transparency and chroma.

Color Index: Pigment Violet 55
Chemical group: Quinacridone

Product Specification

Density: 1.61 g/cm³
Surface Area (BET): 50 m²/g
Oil absorption: 25 ml/100 g

Halogenated: no

Fastness Properties

Chemical Resistance:

(1=poor; 5=excellent)

Acid:	5
Alkali:	5
Lacquer solvents:	5
Ethyl alcohol:	5
Glycols:	5
Ethyl acetate:	5
Methyl ethyl ketone:	4
Mineral spirits:	5
Water:	5
Xylene:	5
Paraffin wax:	NT

Lightfastness:

(1=poor; 8=excellent)

Masstone:	7 – 8
1 – 10 Tint:	7
1 – 25 Tint:	7

Heatfastness:

Coatings:	5:95 Tint	DE < 2.0	200°C / 392°F
------------------	-----------	----------	---------------

Inks:	Metal Deco	15 min (150°C) 30 min (300°C)
--------------	------------	----------------------------------

Plastics:	LDPE 1:19 Warpage 2 % in HDPE	DE < 2.0
------------------	----------------------------------	----------

Weatherfastness (Gray Scale)

(1=poor; 5=excellent)

		Masstone	Tint	Metallic
Coatings	South Florida 5°BB	4 – 5	4	4
Plastics	DIN EN ISO 4892-2	-	-	-

Application Profile

Coatings:

- Automotive	recommended
- Architectural / Deco	recommended
- General Industrial	recommended
- Powder	recommended
- Coil	recommended
- Solvent	recommended
- Waterborne	recommended

Inks:

- Water based	not recommended
- Solvent	not recommended
- UV	not recommended
- Sheed fed	not recommended

Plastics:

Rubber, pPVC, LDPE, PA6, PP, HDPE, PS, PC, PET: not recommended