

23850 Studio Yellow

Product with good fastness to light and weathering for air-drying paints. Because of its pure greenish shade it is particularly suitable for green mixtures. Owing to the high risk of blooming, it is not suitable for stoving enamels.

Product Specification

Chemical Characterization:	Monoazo yellow
Color Index:	Pigment Yellow 3, No. 11710
pH:	5.5 – 8.5
Density:	1.58 g/cm ³
Oil absorption number:	59 ml/100 g
Specific conductivity:	≤ 0.2 mS/cm
Volatile fraction:	≤ 1.0 %
Sieve residue (0,063 mm sieve):	≤ 0.1 % (DIN 53195)
Average particle size:	405 nm
Heat stability:	140°C