

81002 Lascaux® Acrylic Glue 498 HV

Technical Data:

Thermoplastic copolymeric butyl-methacrylate-dispersion, thickened with acrylic ester acid.
The pH-value is stabilized at 8-9 and is treated with preservatives.

Film-formation:

Minimal film-formation temperature:	approx. 5°C
Glass transition temperature:	approx. 13°C
Elongation at break:	approx. 400 %
Minimal sealing temperature:	68 - 76°C
Dry film:	hard elastic

Solubility:

- dilutable with water, after drying: water-insoluble
- permanently soluble in acetone, alcohol, toluene, xylene.
- insoluble in white spirit.

Application:

For light and ageing-resistant, non-cross-linking agglutination such as re-lining, marouflage, lamination, collages etc. Applicable as wet or reactive dry technique, on absorbent and non-absorbent grounds such as paper and cardboard, textiles, wood and fibreboards, polyester boards, gypsum plaster and concrete, glass and acrylic glass, aluminium, etc.

Lascaux Acrylic Glue 498 HV dries as a viscous elastic film, it is extremely tensile. It is suitable for wet and dry application (reactivation with solvents). Standard type for relining and marouflages.

Storage:

Store in tightly closed containers at 5 – 25°C.