

76910 Thickener K 15

Properties	Value
Solid content (DIN EN ISO 3251)	30 %
pH Value (ISO 976)	3.0
Viscosity (ISO 2555)	< 100 mPa.s
Glass transition temperature (ASTM D 3418)	71°C
Density	1.05 g/cm ³
Average particle size	0.1 µm
Ionic adjustment	anionic
Acid value	55 – 65 mg KOH/g

Application:

Thickener for dispersion paints, synthetic resin plasters, glues.

Add carefully by constantly stirring !

The viscosity of the solution increases later – the final fastness is not reached until after 12 hours.