

## 63000 – 63080 Technical Data

	<b>Product</b>	<b>Delivery Form</b>	<b>Viscosity</b>	<b>pH Value</b>	<b>Bloomgrams</b>
63000	Bone Glue <sup>1)</sup>	Pearls	60-70 mPa•s <sup>3)</sup>	5.75 – 7.0	160-180
63021	Hide glue <sup>1)</sup>	Grains	72-88 mPa•s <sup>3)</sup>	5,5-7,5	235-265
63028	Rabbit Skin Glue <sup>2)</sup>	Grains	5,25-5,75 <sup>4)</sup>	5.5 - 6.5	340-360
63045	Technical Gelatine	Powder	115-126 mPa•s <sup>3)</sup>	5.8 – 7.0	340-380
63052	Glue Plates <sup>2)</sup>	Plates	5,25-5,75 <sup>4)</sup>	5.5 – 6.5	340-360
63060	Bookbinder Glue <sup>1)</sup>	Grains	100-120 mPa•s <sup>3)</sup>	6.0 – 7.0	330-370
63080	Fish Glue Blend	Flakes	145-175 mPa•s <sup>3)</sup>	6.0 – 7.0	575-625

<sup>1)</sup> = from bovine collagen

<sup>2)</sup> = The technical properties of this glue correspond to the qualities of historical rabbit glue.

<sup>3)</sup> = mPa•s at 12.50 % and 60°C

<sup>4)</sup> = Engler viscosity